

Acid Pickle/Deruster, Liquid

Powerful surfactants provide deep cleaning
Laser and plasma oxide remover
Effective against rust and heat scale, too
Does not contain phosphates

DESCALE NP is a concentrated acid liquid that will remove rust, heat scale, and corrosion products from ferrous metal parts. **DESCALE NP** can be used in an immersion system or a spray system. **DESCALE NP** can remove oxides formed from laser and plasma cut steel. The **DESCALE NP** treated parts will be prepared for further processing with a surface conversion or a rust preventative application for future processing.

PHYSICAL PROPERTIES

Liquid, clear
Light yellow color
Density: 10.1 lbs/gal

OPERATING CONDITIONS

	Immersion	Spray
Concentration:	10 to 50% by volume	3 to 10% by volume
Temperature:	Unheated to 120°F	100 to 160°F
Time:	5 to 15 minutes	1 to 2 minutes

EQUIPMENT

None of the usual stainless steel alloys are totally resistant to the **DESCALE NP** processing solution. Type 316 stainless steel alloys will provide satisfactory service. We recommend its use for the construction of tanks, piping, pumps, and heat transfer surfaces.



INITIAL CHARGING PROCEDURE

1. Fill the tank to 2/3 of the final volume with clean, cool water.
2. Add the required amount of **DESCALE NP** slowly, with sufficient agitation to ensure thorough mixing.
3. Add cool water to increase the volume to the operating level. The solution is then ready to be heated to operating temperature.

SOLUTION CONTROL

Titration Procedure:

Materials required: 25 ml pipet
125 ml glass flask Automatic burette assembly
1% Phenolphthalein (LIN-001)
1.0N Sodium Hydroxide (LTS-014)

1. Pipet a 25 ml sample of the bath into a 125 ml glass flask.
2. Add 50 mls of deionized/distilled water to flask.
3. Add 8-10 drops of 1% Phenolphthalein Indicator (LIN-001) to flask.
4. Titrate with 1.0N Sodium Hydroxide (LTS-014) until the sample develops a pinkish tinge or hue.

Concentration: mls of 1.0N Sodium Hydroxide (LTS-014) required times the product factor, 0.52, equals the concentration in percent by volume of product in solution.

mls of 1.0N Sodium Hydroxide (LTS-014)	% by volume
3.8	2
7.7	4
11.5	6
15.4	8



REPLENISHING

A bath made up at 5% by volume will have a titration of about 9.6 mls. The titration, bath concentration, should be maintained between 9.1 and 10.1 mls. The addition of 5.0 gallons of the product per 1000 gallons of solution will increase the strength approximately 1.0 ml.

Dissolved Iron Determination

Materials Required: 10 ml pipet
 125 ml glass flask
 50% Sulfuric Acid (LRS-013)
 0.05N Potassium Permanganate (LTS-010)

Titration Procedure for Dissolved Iron:

1. Pipet a 10 ml sample of the bath into a 125 ml glass flask.
2. Add approximately 1 ml of 50% Sulfuric Acid (LRS-013).
3. Titrate with 0.05N Potassium Permanganate (LTS-010) until the solution turns pink, and the pink color persists for 10-15 seconds.
4. Record the numbers of mls required to maintain the pink color for 10-15 seconds as the dissolved iron

mls 0.05N Potassium Permanganate (LTS-010)	% iron
3.6	0.1
7.2	0.2
10.8	0.3
14.4	0.4
18.0	0.5
21.6	0.6

Solution Maintenance:

The dissolved iron content needs to be maintained to produce consistent, acceptable results. The iron content in the **DESCALE NP** solution will increase as production ware is processed. Maintain the iron concentration below 0.4% through the use of an auto-drain technique or through chemical or mechanical remediation. Consult your Coral Consultant



for details. If the iron content becomes greater than 0.5% you will need to discard a portion of the bath, increase the amount of overflow, or increase the concentration of **DESCALE NP** to maintain proper oxide removal.

PRECAUTIONARY INFORMATION

Consult the product Safety Data Sheet for all safety and handling information prior to using this product.

NEUTRALIZATION GUIDELINES

To help adjust the pH of the descale solution back towards neutral, the addition of 0.40 gallons of pH Plus (091-002) will neutralize about 1 gallon of **DESCALE NP**. The pH plus should be added slowly with agitation. Monitor the change in pH closely. Depending on the concentration of descale, heat may be generated during neutralization. Neutralization alone does not satisfy waste discharge or disposal rules, standards and requirements pursuant to Federal, State or Local laws. It is the responsibility of the user of Coral products to ensure compliance with the same.

WASTE DISPOSAL AFTER USE

Check your state, local and federal regulations on waste disposal to ensure compliance before disposing of any Coral product. Consult Coral if you are not sure how to treat this product for waste disposal.

STORAGE

Check your local, state and federal regulations on chemical storage to ensure compliance before receiving and storing Coral products. Generally, we recommend that users employ common sense storage precautions to protect their workers, first responders, facilities, sewers, and the environment from accidental spills and leaks of hazardous chemical products. Contact Coral for specific storage precautions not contained herein.



Revision Date: 4/28/2020



1915 Industrial Avenue

Zion, Illinois 60099

PH: 847.246.6666

FX: 847.246.6667

www.coral.com

To the best of our knowledge the information in this bulletin is true and accurate. However, since application of the products described herein is beyond the control both the product and information is offered without guarantee as to their use. We assume no liability for incidental, consequential, or direct damages of any kind, no matter the cause, including negligence. "Nothing contained within this operating bulletin shall be taken as a recommendation to use any product in violation of any patent rights." The Company reserves the right to make changes to the data herein without notice.