

TECHNICAL DATA SHEET

LUPREP™ 601 WATER SOLUBLE RUST PREVENTIVE

LUPREP™ 601 is a water-based rust preventative designed to protect metal surfaces against humidity and corrosion. It provides temporary indoor protection of ferrous and non-ferrous metal surfaces.

Applications

Short term rust preventive applications.

Recommendation for Use

LUPREP™ 601 can be diluted with water from 5:1 - 20:1. It mixes easily with water and dries to a clear film. Recommended method of application is dipping or spraying. LUPREP™ 601 can also be used following any HOUGHTO-PREP™ conversion coating to provide in-plant corrosion protection of steel surfaces prior to painting or powder coating. The use concentration of the LUPREP™ 601 in this type of application should be 0.5 - 2.0 % by volume, as not to cause any subsequent coating adhesion problems.

Temperature range for use with this product is ambient to 140°F.

Benefits

- Dries to a clear, non-staining film
- Maintains hard water stability
- Contains no sodium nitrite
- Provides excellent wetting on ferrous metals

Health, Safety and Handling

Please consult the Safety Data Sheet (SDS) for information on storage, safe handling and disposal. The conditions or methods of handling, storage, use and disposal of the product are beyond our reasonable control - we assume no liability for any ineffectiveness of the product or any injury or damage, arising out of or in connection with these conditions.

Properties

PROPERTY	TYPICAL VALUE	UNIT
Appearance	Clear Fluid	
Appearance dilution	Clear Fluid	
Odor	Mild	
Weight per US Gallon at 25°C	8.5	
Specific Gravity	1.04	
pH concentration	10.2	
pH at 5:1 dilution	9.9	

All reasonable care has been taken to ensure this publication is accurate upon issue. Such information may be affected by changes subsequent to issue. This Technical Data Sheet is to be used solely for this product. Prior to any use, consult the Safety Data Sheet (SDS) for information on hazard risks and product use parameters. All liability and all warranties express or implied are hereby excluded as to product performance results, the accuracy of these data including any warranty of merchantability or fitness for any purpose. 89560100

