# TECHNICAL DATA SHEET

# **RUST VETO® 342**

#### TRANSLUCENT COATING FOR HEAVY-DUTY RUST PROTECTION

RUST VETO® 342 is solvent-based rust preventive that leaves an amber, translucent, waxy dry film.

RUST VETO® 342 offers good protection to steel against salt spray and outdoor weathering.

36+ months indoor corrosion protection and 12 months outdoor protection leaving a translucent, waxy film. FCA 47-400-0791 and CATERPILLAR 1E0355 approvals.

### **Applications**

Apply by dip, brush or spray.

#### **Recommendation For Use**

RUST VETO® 342 protects iron and steel from rust for lengthy storage indoor and outdoor.

Numbers and lettering can be clearly seen through the film when the solvent has evaporated from it. This makes it possible to easily identify codes on items left in storage for long periods.

#### **Benefits**

- Easy to apply
- Good for shed, outdoor and salt spray protection
- Chloride free
- Rapid drying permits handling of parts shortly after application which expedites process flow and packaging.

#### Health, Safety and Handling

Please consult the Safety Data Sheet (SDS) for information on storage, safe handling and disposal. The conditions or methods of handling, storage, use and disposal of the product are beyond our reasonable control - we assume no liability for any ineffectiveness of the product or any injury or damage, arising out of or in connection with these conditions.

## **Typical Physical Properties**

PROPERTY	TYPICAL VALUE	UNIT
Type of film	Amber, translucent, non-tacky, waxy dry film	
Film Thickness	2.5	mil
Non-Volatile	55	%
Flash Point	108	° F
Removal	Removable with petroleum solvent	
Coverage	400	sq ft / gal

All reasonable care has been taken to ensure this publication is accurate upon issue. Such information may be affected by changes subsequent to issue. This Technical Data Sheet is to be used solely for this product. Prior to any use, consult the Safety Data Sheet (SDS) for information on hazard risks and product use parameters. All liability and all warranties express or implied are hereby excluded as to product performance results, the accuracy of these data including any warranty of merchantability or fitness for any purpose. 21342000

